

**Pale 1000 – Blown Castor Oil**  
Technical Data Sheet



**Product Identification**

These non-drying castor polymers, commonly known as blown oils have increasing viscosities resulting from oxidative and crosslink polymerization at the double bonds and hydroxyl groups.

Oxidative polymerization of castor oil yields products with increased viscosities and decreasing solubility in aliphatic solvents, increasing compatibility with various resins and improved ability to wet and disperse pigments while imparting solvent and abrasion resistance to lacquer systems. The polymerized oils are used to plasticize a variety of resins in adhesive and sealant systems, inks and hot melts. The heavier viscosity polymerized oils are processing aids and plasticizers for rubber polymers, imparting oil and solvent resistance.

**Physical Properties**

<u>Property</u>	<u>Value</u>
Acid Value	20
Color, Gardner	8
Density, lbs./gal, 25°C	8.47
Fire Point, COC, °F	590
Flash Point, COC, °F	400
Hydroxyl Value	139
Iodine Value	59
Pour Point, °F	25
Refractive Index	1.4820
Saponification Value	230
Specific Gravity, 25°C/25°C	1.018
Viscosity, 25°C, Stokes	170
Volatile, %	0.3

**Applications**

- Adhesives, caulks and sealants
- Water fighters, inks, lubricants
- Lacquer plasticizers, polishes, rubber compounding
- Hydraulic fluids, tack rags, leather dressing, gasket cements

For toxicity or regulatory information please consult the Material Safety Data Sheet.

*Information contained in this technical data sheet is believed to be accurate. Vertellus Performance Materials Inc. assumes no liability and makes no warranty or representation that the information is correct or complete and EXPRESSLY DISCLAIMS ALL REPRESENTATIONS OR WARRANTIES OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Final determination of suitability of any material and issues of patent infringement is the sole responsibility of the user who alone knows the conditions of intended use. Our customers should ensure that any product incorporating a Vertellus ingredient is safe for its intended use pursuant to applicable law and that any necessary disclosures to consumers have been made.*

Vertellus Performance Materials Inc., 2110 High Point Road, Greensboro, NC 27403 USA  
 USA Tel: 800-227-2436 USA Fax: 336-854-4058 USA Email: VPM-TechServices@vertellus.com  
 Web: [www.vertellus.com](http://www.vertellus.com)