



Wayne Pigment Corp.
300 South Barclay Street Milwaukee, Wisconsin 53204
Phone 414/225-2400 FAX 414/225-2410
www.waynepigment.com
E-mail: genoffice@waynepigment.com

2011NT1.C03
Page 1 of 1

Mirrorstop 201
Corrosion Inhibitive Pigment

General Features:

- Advanced Multi-Component, Multi-Phase Hybrid System for Mirror Baking Coatings
- Lead Free
- More Effective Corrosion Inhibitive Mechanism
- Comprises Distinctly Different Corrosion Inhibitive Species and Formulation
- Intellectual Property Rights Held by Wayne Pigment Corp.

Characterized by:

- Synergistic behavior with Respect to Inhibition of Ag, Fe, and Cu Corrosion
- Improved Corrosion Inhibitive Performance

Recommendations:

- Solvent Based Systems
- Ag, Fe, Cu, Galvanized
- Lead Cyanamide Replacement

The recommendations made herein are based on our research and on the research of others; and are believed to be accurate. No guarantee of the accuracy is made, however, and the products discussed are sold without warrant, expressed or implied, and upon the condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes.

CORROSION INHIBITIVE PIGMENT FOR MIRROR BACK COATINGS

<u>Characteristic Parameters</u>	<u>Typical Values</u>
Appearance	White Powder
Specific Gravity	2.50 - 2.70
Bulking Value (gal/lb)	0.044 - 0.048
Oil Absorption (lbs/100 lbs)	22 -28
pH	7.5 -8.5
Moisture, % (loss on ignition, 110 •C)	< 5.0

The recommendations made herein are based on our research and on the research of others; and are believed to be accurate. No guarantee of the accuracy is made, however, and the products discussed are sold without warrant, expressed or implied, and upon the condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes.