



Wayne Pigment Corp.
300 South Barclay Street Milwaukee, Wisconsin 53204
Phone 414/225-2400 FAX 414/225-2410
www.waynepigment.com
E-mail: genc@wpc@waynepigment.com

233INTLC03
Page 1 of 1

Basic Zinc Chromate 233
Corrosion Inhibitive Pigment

General Features:

- Zinc Tetroxy Chromate for Vinyl Wash Primers
- Excellent Dispersibility
- Improved Solubility
- Competitively Priced

Characterized by:

- High Chrome Content
- Excellent Lot to Lot Quality Consistency

Recommendations:

- See pertinent documentation

The recommendations made herein are based on our research and on the research of others; and are believed to be accurate. No guarantee of the accuracy is made, however, and the products discussed are sold without warrant, expressed or implied, and upon the condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes.

Corrosion Inhibitor for Vinyl Wash Primer Applications

<u>Characteristic Parameters</u>	<u>Typical Values</u>
Appearance	Yellow Powder
Specific Gravity	3.45
Bulking Value (gal/lbs)	0.035
pH	6.0 - 8.0
Oil Absorption (lbs/ 100 lbs pigment)	38 - 42
Moisture, %	< 1.5

The recommendations made herein are based on our research and on the research of others; and are believed to be accurate. No guarantee of the accuracy is made, however, and the products discussed are sold without warrant, expressed or implied, and upon the condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes.